

DUST PALLIATIVE BITUMENS

PROPERTY	TSD3	TSD8	TEST METHOD
1) Kinematic viscosity @ 60°C, cSt	3000 – 6000	T e m p o r a r y D i s c o n t i n u e d	ASTM D 2170
2) Dynamic viscosity at 60 °C, mPa.s c	3000 – 7000		ASTM D 4402
3) Flash – point ,°C	38 Min		ASTM D 93
4) Water, % by mass or volume	0,2 Max		ASTM D 95
3) Distillation @ 101,325 kPa @ by volume of total distillate to 360 °C			
to 190°C	-		ASTM D402
to 225°C	0 – 25		ASTM D402
to 260°C	0 – 40		ASTM D402
to 316°C	35 – 80		ASTM D402
4) Residue from distillation to 360°C, % volume of original sample	80 Min		ASTM D402
5) Viscosity at 60 °C on residue from distillation, Pa.s	30 Min	ASTM D 4402	
6) Application temperature °C	135 – 140		
7) Typical density in kg / litre :			
at 20°C	0,991	ASTM D 3142 / D 3142 M-11	
at application temperature	0,916	ASTM D 3142 / D 3142 M-11	
7) Uses	Sand seals on unprimed bases and covered with river/crusher sand		
8) Cleaning and handling	Refer Safety Data Sheets		

NOTE : This data is issued as a guide to the use of the product(s) concerned and whilst every effort is made to ensure the accuracy of the text which is in accordance with the latest technical developments, we cannot accept responsibility for any work carried out with our materials as we have no control over the method of application used or condition of site involved. In view of the constant research and development being undertaken in our laboratories we advise customers in their own interest to ensure that this data sheet has not been superseded by a more up-to-date publication. All products are sold subject to our standard conditions of sale which are available on demand.

Revised by: J. Van Heerden

Approved by : J. Muller

Date : December 2017