



(Pty) Limited

PRODUCT SPECIFICATIONS

DATA SHEET NO : E-13

TOSAS ENVIRONMENTALLY FRIENDLY REJUVENATOR 60%

PROPERTY	EFR 60	TEST METHOD
1) Viscosity @ 50°C, Saybolt Furrol seconds	15 - 50	TOSAS TEST TS – 3 (12) TOSAS TEST TS – 3 (12)
2) Binder content, % (m/m)	60 – 63	-
3) Fluxing agent content, % (m/m) of binder, Max	5	
4) Residue on sieving, g/100 ml, Max	0,25	TOSAS TEST TS – 3 (12)
5) Particle charge - Modified procedure	Positive	TOSAS TEST TS – 3 (9a)
6) Binder deposit on the cathode after 30 min. g, Min	1,0	TOSAS TEST TS – 3 (9a)
7) Sedimentation after 60 complete rotations	Nil	TOSAS TEST TS – 3 (13)
8) Typical density in kg/litre	1,000	ASTM D 3142 / D 3142 M-11
9) Uses	Rejuvenation of aged / dry road surface	
10) Cleaning and handling	Refer Safety Data Sheet	
11) NOTE: Typical application rate for this product would be 0.35 l/m² neat or diluted 50:50 @ an application rate of 0.7 l/m²	Refer Safety Data Sheet	

NOTE : This data is issued as a guide to the use of the product(s) concerned and whilst every effort is made to ensure the accuracy of the text which is in accordance with the latest technical developments, we cannot accept responsibility for any work carried out with our materials as we have no control over the method of application used or condition of site involved. In view of the constant research and development being undertaken in our laboratories we advise customers in their own interest to ensure that this data sheet has not been superseded by a more up-to-date publication. All products are sold subject to our standard conditions of sale which are available on demand.

Revised by: J. Lambert

Approved by : J. Muller

Date : December 2017