

**CATIONIC MIX GRADE EMULSIONS (SANS 4001 BT-4)**

PROPERTY	KMS 60	KMS 65	STOCKMIX 65	TEST METHOD <sup>1</sup>
1) Viscosity @ 50°C, Saybolt Furol seconds	20 - 50	51 - 200	51 – 200	SANS 4001 BT- 4 (5.2)
2) Binder content, % (m/m)	60 - 63	65 - 68	65 – 68	SANS 4001 BT- 4 (5.2)
3) Fluxing agent content, % (m/m) of binder, Max.	5 - 10	5 - 10	5 - 10	SANS 4001 BT- 4 (4.4)
4) Residue on sieving, g/100 ml, Max.	0,25	0,25	0,25	SANS 4001 BT- 4 (5.3)
5) Particle charge – Standard procedure (10 mA)	Positive	Positive	Positive	SANS 4001 BT- 4 (5.4)
6) Binder deposit on the cathode after 30 min. g, Min.	-	-	-	SANS 4001 BT- 4 (5.4)
7) Sedimentation after 60 complete rotations	Nil	Nil	Nil	SANS 4001 BT-3 (5.6)
8) Typical density in kg / litre @ 60 ° C	1,000	1,000	1,000	ASTM D 3142 / D 3142 M-11
9) Aggregate coating / water resistance test	Pass	Pass	-	SANS 4001 BT-3 (5.5)
10) Uses	Cold premix using 6.7 mm Chips – Pothole patching			
11) Cleaning and handling	Refer Safety Data Sheets			

<sup>1</sup> Reference method is ASTM D244

**NOTE :** This data is issued as a guide to the use of the product(s) concerned and whilst every effort is made to ensure the accuracy of the text which is in accordance with the latest technical developments, we cannot accept responsibility for any work carried out with our materials as we have no control over the method of application used or condition of site involved. In view of the constant research and development being undertaken in our laboratories we advise customers in their own interest to ensure that this data sheet has not been superseded by a more up-to-date publication. All products are sold subject to our standard conditions of sale which are available on demand.

Revised by: J. van Heerden

Approved by: J. Muller

Date : December 2017