



(Pty) Limited

PRODUCT SPECIFICATIONS

DATA SHEET NO : E-22

NANO MODIFIED CATIONIC SPRAY GRADE EMULSIONS TACK COAT

PROPERTY		TEST METHOD
1) Viscosity @ 50°C, Saybolt Furrol seconds	10 - 30	SANS 4001 BT- 4 (5.2)
2) Binder content, % (m/m)	30%	SANS 4001 BT- 4 (5.2)
3) Nano Modifier, %	-	
4) Residue on sieving, g/100 ml, Max	0,25	SANS 4001 BT- 4 (5.3)
5) Particle charge - Modified procedure	Positive	SANS 4001 BT- 4 (5.4)
6) Sedimentation after 60 complete rotations	Nil	SANS 4001 BT – 3 (5.6)
7) Typical density in kg/litre	1,000	ASTM D 3142 / D 3142 M-11
8) Uses	Dilute application for Nano-Tack	
9) Cleaning and handling	Refer Safety Data Sheet	
10) NOTE:		

NOTE: This data is issued as a guide to the use of the product(s) concerned and whilst every effort is made to ensure the accuracy of the text which is in accordance with the latest technical developments, we cannot accept responsibility for any work carried out with our materials as we have no control over the method of application used or condition of site involved. In view of the constant research and development being undertaken in our laboratories we advise customers in their own interest to ensure that this data sheet has not been superseded by a more up-to-date publication. All products are sold subject to our standard conditions of sale which are available on demand.

Revised by: J. van Heerden

Approved by: J. Muller

Date: December 2017