



Tosas Pothole Patch

Product: Nominal 6.7mm Open Graded Cold Mix Asphalt

Standard Test Methods	Description of Property	Result	
SANS 3001 – AS10:2011	Bulk Density of Compacted Asphalt	1929 kg/m ³	
	Void Content of Compacted Asphalt	21.8%	
SANS 3001 – AS11:2011	Maximum Void-less Density	2466 kg/m ³	
SANS 3001 – SA20:2011	Binder Content of an Asphalt Mix	4.3%	
	Grading Analysis – Cumulative % passing	9.5mm	100
		6.7mm	92
		4.75mm	43
		2.36mm	15
		1.18mm	10
		0.600mm	7
		0.300mm	6
		0.150mm	5
		0.075mm	2.8

The above tests were performed in National Asphalt’s laboratory at Bon Accord, Pretoria. Properties such as stability, flow, immersion index and indirect tensile strength are not applicable to open graded asphalt mixes. Application rate is 2 bags covers 1m³

NOTE : This data is issued as a guide to the use of the product(s) concerned and whilst every effort is made to ensure the accuracy of the text which is in accordance with the latest technical developments, we cannot accept responsibility for any work carried out with our materials as we have no control over the method of application used or condition of site involved.

In view of the constant research and development being undertaken in our laboratories we advise customers in their own interest to ensure that this data sheet has not been superseded by a more up-to-date publication. All products are sold subject to our standard conditions of sale which are available on demand.

Revised by: J. Van Heerden

Approved by: J. Muller

Date: December 2017